

## GREIBOTAN D-67

Resin for the retannage of chrome-leather to improve fullness

### Characteristics

Base:	Formulated dicyandiamide resin
Appearance:	Fine light beige powder
Concentration:	Above 94%
pH :	8,5 - 10,5 (50 g/l aqueous solution)
Charge:	Anionic
Recommendation for dissolving:	Greibotan D-67 is added undissolved.
Light fastness:	Good
General:	Greibotan D-67 is a resin tanning agent used in the retannage of chrome-tanned leather. It improves the fullness especially in the belly parts without affecting the character of the chrome leather.
Safety:	If Greibotan D-67 is handled according to normal industrial hygiene practice for chemicals, no special precautions are necessary.
Shelf-life:	Maximum 2 years.
Handling:	The product must be stored under dry conditions.
Packing:	25 kg in plastic sacks on a pallet holding 625 kg net weight.

All information quoted above is based on our experience and actual know-how but is given without guarantee and obligation. Recommendations on the application and use of our products, should be adapted to the particular working-conditions and other materials employed.

## GREIBOTAN D-67

Resin for the retannage of chrome-leather to improve fullness

### Application

Leathers retanned with Greibotan D-67 show a very tight grain with a round feel and can easily be finished.

In addition the printing and polishing properties of the leather are improved.

Greibotan D-67 has no negative influence on the waterproofing if applied in quantities of 3 - 5% together with the retanning agents.

All information quoted above is based on our experience and actual know-how but is given without guarantee and obligation. Recommendations on the application and use of our products, should be adapted to the particular working-conditions and other materials employed.