

GREIBOTAN M-48

Resin for the retannage of chrome-leather to improve fullness

Characteristics

Base:	Melamine based resin with inorganic fillers
Appearance:	Light beige powder
Concentration:	Minimum 94%
pH :	9,0 - 11,0 (10% aqueous solution)
Charge:	Anionic
Recommendation for dissolving:	Greibotan M-48 is added undissolved.
Light fastness:	Good
General:	Greibotan M-48 is a resin tanning agent used in the retannage of chrome-tanned leather. It improves the fullness especially in the belly parts without affecting the character of the chrome leather.
Safety:	If Greibotan M-48 is handled according to normal industrial hygiene practice for chemicals, no special precautions are necessary.
Shelf-life:	Maximum 2 years.
Handling:	The product must be stored under dry conditions.
Packing:	25 kg in plastic sacks on a pallet holding 625 kg net weight.

All information quoted above is based on our experience and actual know-how but is given without guarantee and obligation. Recommendations on the application and use of our products, should be adapted to the particular working-conditions and other materials employed.

GREIBOTAN M-48

Resin for the retannage of chrome-leather to improve fullness

Application

Leathers retanned with Greibotan M-48 show a very tight grain with a full feel and can easily be finished.

In addition the printing and polishing properties of the leather are improved.

Greibotan M-48 does not show any negative influence on waterproofing results if applied in quantities of 3 - 5% together with the retanning agents.

All information quoted above is based on our experience and actual know-how but is given without guarantee and obligation. Recommendations on the application and use of our products, should be adapted to the particular working-conditions and other materials employed.