

## GREIBOSOL HPI

### Fatliquoring agent

GREIBOSOL HPI is a fatliquoring agent for water resistant and soft leathers as well as for chrome and combination tanned leathers. Leathers fatliquored with GREIBOSOL HPI have a silky, smooth handle. Its very good light fastness makes GREIBOSOL HPI also suitable for white or pastel shade leathers. On suede leathers, a nice lustre is obtained.

#### Characteristics

Base:	Combination of sulphited synthetic fats, polymeric components and emulsifiers
Appearance:	Liquid, white
Concentration:	Approx. 50 %
Chemical treatment:	Sulphited
pH of a 10 % solution:	7 - 8
Charge:	Anionic

#### Properties

Light fastness:	Very good
Heat resistance:	Good
Storage life:	1 year (at room temperature) The optimal storage temperature is between 15 - 30 °C. GREIBOSOL HPI should be protected from frost. The product should be stirred thoroughly prior to use.

All information quoted above is based on our experience and actual know-how but is given without guarantee and obligation. Recommendations on the application and use of our products, should be adapted to the particular working-conditions and other materials employed.

## GREIBOSOL HPI

### Fatliquoring agent

Stability in:

- chrome tanning floats:      Not stable

Method of diluting:              Stir water at 60 °C into the product.

### Application

In addition to its very good softening properties GREIBOSOL HPI, applied in a suitable process, results in good water-resistance. The best water-resistant effects are obtained by subsequent treatment with suitable cationic "capping" agents, e.g. chromium sulphate. (Cationic "capping" should be realized in a fresh bath.)

GREIBOSOL HPI can be combined with other anionic and non-ionic fatliquoring agents. However, depending on the customers' requirements, additional fatliquoring agents may not be necessary.

All information quoted above is based on our experience and actual know-how but is given without guarantee and obligation. Recommendations on the application and use of our products, should be adapted to the particular working-conditions and other materials employed.