

GREIBOSOL SFH

Fatliquoring agent - pickle, tanning & main fatliquor

GREIBOSOL SFH is the appropriate product for soft leather types, such as soft upper leathers for shoes, nappa for boots or types of shoes softies, upholstery as well as car upholstery.

Characteristics

Base:	Marine oils of selected high quality
Appearance:	Reddish brown oil, possible with sediments
Concentration:	Approx. 82 %
Chemical treatment:	Sulphited
pH of a 10 % solution:	Approx. 6 - 8
Charge:	Anionic

Properties

Light fastness:	Moderate
Heat resistance:	Moderate
Storage life:	Approx. 1 year Resistant against frost. After frost exposure heat to approx. 20°C and homogenize by means of stirring.
Stability in:	
- chrome tanning floats:	Stable
Method of diluting:	GREIBOSOL SFH is diluted with water at 60 °C whilst stirring, it will give a fine dispersed emulsion. The product can be added undiluted.

All information quoted above is based on our experience and actual know-how but is given without guarantee and obligation. Recommendations on the application and use of our products, should be adapted to the particular working-conditions and other materials employed.

GREIBOSOL SFH

Fatliquoring agent - pickle, tanning & main fatliquor

Because of its high electrolyte stability, GREIBOSOL SFH can also be used for compact retanning. GREIBOSOL SFH is the given fatliquoring agent for vegetable tanned leathers.

Application can be made at all production stages - in pickle, tanning, pre-fatliquor as well as main fatliquor.

Initially for use in pickle:

1 - 2 % GREIBOSOL SFH is recommended possibly combined with 0.2 - 0.5 % GREIBOPOL STE. (% based on pelt weight).

Recipes

Prefatliquoring

in pickle/ tanning:	1.0 - 2.0 %	GREIBOSOL SFH
	0.2 - 0.5 %	GREIBOPOL STE
		(% data based on pelt weight)

Prefatliquor in chromous:	2.0 %	GREIBOSOL SFH
---------------------------	-------	---------------

retanning and/or neutralization:	0.5 %	GREIBOPOL STE
----------------------------------	-------	---------------

Main fatliquor:	5.5 %	GREIBOSOL SFH
-----------------	-------	---------------

Upper leather:	5.5 %	GREIBOSOL SLM
----------------	-------	---------------

Car upholstery:	7.0 %	GREIBOSOL SFH
	0.5 %	GREIBOPOL STE

All information quoted above is based on our experience and actual know-how but is given without guarantee and obligation. Recommendations on the application and use of our products, should be adapted to the particular working-conditions and other materials employed.